



POLYMER FORTIFIED CEMENTITIOUS SANDED GROUT




BENEFITS

- For Interior and Exterior, Floor and Wall Application
- For Joints 3mm - 12mm.
- Water and Shock Resistant
- Superior Colour Fast Pigments
- Highly Chemical Resistant
- Ultra Strong and Durable
- Multi Colour Options
- Suitable for all types of Tiles, Stones and Bricks.

SPECIFICATIONS

Colour	36+ Colours available (Refer Colour Chart)
Mixing	For better performance, in place of Water add 150 - 200ml of ADICRETE 1776 Cement Grout Admixture or normal Clean Water for every 1kg of Grout powder
Coverage	Depends on Tile Size, Joint Width and Depth (Refer Coverage Chart)
Pot Life	1 Hour
Foot Traffic	48 Hours
Packing	1kg, 5kg & 20kg

APPLICATION

								
Clean Tiles Before Grouting	Fill the Grout Joints Completely	Use the Grout Float to Remove All the Excess	Allow Grout to Stiffen in the Joint	Use Slightly Damp Universal Sponge Board for the First Wash	Ensure You Use Clean Water	Avoid Using Water Containing Polymer Residue	Clean Off Remaining Residue	Give a Final Wash Down After Two Hours

PRECAUTION

1. Ensure tile adhesive has fully set, Minimum 24hrs during time is recommended. 2. Ensure open joints are clear from excess adhesive and are protected from contamination, dry and free from loose debris. 3. Be consistent with the amount of clean cold water used with the cement-based grout from mix to mix when grouting larger areas as indicated on Grout packaging. 4. Lighting conditions during the installation of tile fixing and grouting should not be different from the final permanent lighting, check the grout colour in the final lighting conditions. 5. Check colour consistency when using the same grout if applied between different tile types i.e. porous bodied or porous stone tiles vs. porcelain or denser stone. 6. Do not use in temperatures below 5°C or in damp conditions. 7. Site conditions can affect drying times such variance should be allowed for.